

1050 aluminum drilling entry sheet

PRODUCT INTRODUCTION

Haomei's [1050 aluminium drilling entry sheet](#) are manufactured with state-of-the-art equipment which matches international standards. Tight thickness tolerance, flatness, dimensional accuracy and grease-free surface and hardness optimal for burr-free drilling required in the manufacture of PCB are ensured.

Alloy	Temper	Thickness (mm)	Width (mm)	Length (mm)
1050 aluminum drilling entry sheet	O,H12,H14,H16, H18,H19,H22,H24, H26,H28,H32, H34,H36,H38	0.2-4.5	100-2600	500-16000

Specification

Aluminum Drilling Entry Sheet										
Alloy	Temper		Specification(mm)							
			Thickness	Width			Length			
1050	H18		0.14~0.18	1244			1092 1041 940			
				1220			1067 1016 914			
MECHANICAL PROPERTY										
Alloy		Temper		Thickness(mm)		U.T.S(Mpa)		Elongation(%)		
1050		H18		0.14-0.18		170-190		>=2		
TOLERANCE										
Thickness(mm)		Width(mm)		Length(mm)		Squareness (mm)				
+/-0.005mm		1		1		<=2				
Chemical Composition limits(WT.%)										
Alloy	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Al
1050	0.95		0.05~0.20	0.05	-	-	-	0.10	-	Remains